

Product Specifications

Caliper (mils/ µm)	Basis Weight	Brightness (UV Included)	Thermal Response - Nominal				Gurley Stiffness Nominal (mg)		Elmendorf Tear Nominal (g)		Parker Print Surf
			Static - (°C ± 5°)		Dynamic - Atlantek 400 (mJ/mm2)		MD:	CD:	MD:	CD:	
			0.2 ODU	87	0.2 ODU	5.9					
3.20 ± 0.3/81 ± 8	17 x 22— 500 (lbs)	>85	0.2 ODU	87	0.2 ODU	5.9	100	50	50	50	<2.20
	18.7 ± 1.0		1.0 ODU	72	1.0 ODU	8.9					
	g/m2		Max. Density	1.28	Max. Density	1.45					
	70.3 ± 3.5		Required Temp.	149	Energy Req.	16.0					

Features:

- Bond-like feel
- Bright white appearance
- Flexographic printable front and back
- Lithographic printable back side only

Ideal For:

- Point-of-sale
- ATM receipts
- Kiosks
- Parking receipts

Environmental Characteristics:

- Produced without the use of bisphenol A (BPA)

