

# Alpha<sup>®</sup> 400-2.3



## Product Specifications

Caliper (mils/ µm)	Basis Weight	Brightness (UV Included)	Thermal Response - Nominal				Gurley Stiffness Nominal (mg)		Elmendorf Tear Nominal (g)		Parker Print Surf
			Static - (°C ± 5°)		Dynamic - Atlantek 400 (mJ/mm <sup>2</sup> )		MD:	CD:	MD:	CD:	
			0.2 ODU	84	0.2 ODU	4.9					
2.30 ± 0.15/58 ± 4	17 x 22— 500 (lbs)	>85	0.2 ODU	84	0.2 ODU	4.9	28	15	31	35	<2.00
	12.7 ± 0.8		1.0 ODU	131	1.0 ODU	8.3					
	g/m <sup>2</sup>		Max. Density	1.21	Max. Density	1.54					
	47.8 ± 2.9		Required Temp.	148	Energy Req.	16.0					

### Features:

- Good general imaging
- Graphics and logo imaging

### Environmental Characteristics:

- Produced without the use of bisphenol A (BPA)

### Ideal For:

- Economy point-of-sale for retail use
- ATM receipts
- Printer
- Parking receipts
- Facsimile
- Calculator
- Gas pump receipts

