



A CSW Industrials Company

RECTORSEAL BLUE+™

Non-setting Pipe Thread Sealant

Description

RectorSeal BLUE+ is a non-hardening thread sealant containing PTFE plus synthetic fibers. These fibers dispersed in a resinous base combined with inert mineral fillers provide maximum sealing performance. Its low coefficient of friction allows tighter joint makeup with lower torque. It also breaks out easily without galling, seizing, or damaging threads. It is excellent for service where immediate pressurization is necessary. RectorSeal® BLUE+is non-toxic in accordance with NSF Standard 61. In addition, it is approved and listed with the Canadian Standards Association (CSA).



Applications

RectorSeal BLUE+can be used on a variety of metal and plastic piping including iron, galvanized steel, stainless steel, brass, copper, aluminum, polyethylene, reinforced fiberglass, PVC, ABS and CPVC including FlowGuard Gold®.*

RectorSeal BLUE+is recommended for pipe carrying:

- · Acids, dilute
- · Air, compressed
- Aliphatic solvents
- · Ammonia, gaseous and liquid
- · Caustics, dilute
- Cutting oils (low aromatic)
- Heating oils
- · Helium, gaseous
- Hydraulic oils
- · Hydrogen, gaseous
- · Inert gases, gaseous
- Kerosene

- Liquified petroleum gases (butane, propane, mixtures)
- · Natural gas
- · Nitrogen, gaseous
- Refrigerants
- · Soap, liquid
- Vegetable oils
- · Water (hot or cold) Mineral oils

Characteristics | Features

- PTFE enriched
- Allows immediate pressurization
- For use with potable water (hot or cold)
- Non-setting and will not dry out in the can
- Formulated for plastic and metal pipe
- · Smooth easy application
- · Non-flammable
- · Non-separating
- Lubricates and protects threads
- · Low odor
- Lead free and contains no other metals
- For pressures up to 10,000 psi (liquids) and 2,000 psi (gases)

Not recommended for oxygen, chlorine and other oxidizers.

Packaging

Code	Size	Qty. per Case	Lbs. per Case	Cubic Feet
31633	1/4 Pint Brush Top (118 ml)	24 Cans	12	0.18
31553	1/2 Pint Brush Top (237 ml)	24 Cans	21	0.45
31433	Pint Brush Top (473 ml)	12 Cans	19	0.43

Instructions

- Step 1 Stir before using. Wipe threads clean.
- Step 2 For pipe diameters up to 11/4", apply to male threads only. For larger sizes, apply to both male and female threads.
- Step 3 Join and tighten pipe to ANSI Standards. Piping may be placed into service immediately.

For additional technical information, call toll free 1-800-231-3345.

Precautions

FOR CHEMICAL EMERGENCY, SPILL, LEAK, FIRE EXPOSURE OR ACCIDENT, CALL CHEMTREC - DAY OR NIGHT 1-800-424-9300

PRECAUTIONS: Do not take internally. Do not burn - fumes may be harmful. Wash after handling.

FIRST AID: For any overexposure, get immediate medical attention after first aid is given. EYES-Flush 15 minutes with clean water. SKIN-Wash with soap and water. INHALATION-Remove to fresh air. INGESTION-Only if conscious, give large amounts of water and INDUCE VOMITING. FIRE AND SPILLS: Use water fog, CO2, foam, or dry chemicals. Wipe up spills to prevent footing hazard. STORAGE AND HANDLING: Keep container closed when not in use. Do not reuse empty container.

KEEP OUT OF REACH OF CHILDREN.

For additional information, refer to Safety Data Sheet.

Specifications

Wt/Gal @ 77°F	9.3 ± 0.5 lbs/gal.	
VOC	0 g/L	
Flash Point SETA CC	Greater than 300°F (149°C)	
Non-volatiles	100%	
Color:	Blue	
Shelf Life	2 years	
Federal Specification	TT-S-1732	

Approvals











FBC™ System Compatible* indicates that this product has been tested, and is monitored on an ongoing basis, to assure its chemical compatibility with FlowGuard Gold®, BlazeMaster® and Corzan® piping systems and products made with TempRite® Technology. The FBC System Compatible Logo, FBC™, FlowGuard Gold®, BlazeMaster®, Corzan® and TempRite® are trademarks of Lubrizol Advanced MAterials.

Meets ANSI LC 7-2009 Working Temperature Range -40°F to 125°F. Maximum Working Pressure: 125 psi. For Use With Natural Gas (VAPOR STATE ONLY). Use on Steel, Galvanized Steel, Iron, Brass, Copper and Aluminum. For Pipe Size Up to And Including 11½" inch.

Suggestions and recommendations covering the use of our products are based on our past experience and laboratory findings. However, as we have no control as to the methods and conditions of application, we only assume responsibility for the uniformity of our products within manufacturing tolerances.

Limited Warranty

RectorSeal, LLC makes the Limited Express Warranty that when the instructions for storage and handling of our products are followed we warrant our products to be free from defects. THIS LIMITED EXPRESS WARRANTY IS EXPRESSLY IN LIEU OF ANY OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, AND OF ANY OTHER OBLIGATION ON THE PART OF RECTORSEAL, LLC. The sole remedy for breach of the Limited Express Warranty shall be the refund of the purchase price. All other liability is negated and disclaimed, and RectorSeal, LLC shall not be liable for incidental or consequential damages.